

RP2550

100% recycled PVC pulverized into a 20 mesh powder and blended in large quantities to ensure consistency. Primarily used as a substrate in fence, piping and thick profile applications with or without a capstock layer and processed by twin screw extrusion. NEW - Pellets now available.

General Property	Procedure / Method	Typical Value
Form		Pulverized Powder / Pellet
Color	CIELab, D65, 10 degree observer or visual	Earth Tone / Grey
Sieve Analysis	% retention on 20 mesh	4%
	% retention on 120 mesh	97%
Specific Gravity	ASTM D-792	1.48
Bulk Density	ASTM D1895	32 lbs/ft ³
Tensile Strength	ASTM D 1990, Type I [3mm, 2 in/min]	6,000 lbs/in ²
Tensile Impact	ASTM D1822, Type S [3mm]	30 ft-lb/in ²
Drop Impact Resistance	ASTM D4226, 70 F, 8# wt, ½" conical tup. Maximum value on a 2" strip recorded	1.0 in lbs/mil
Heat Deflection Temperature	ASTM D 648-85, under load	160 F
Flame Rating	UL 94 (3mm)	V-0
Hot Wire Ignition	ASTM D3874	PLC <1

Rev. 2

Return Polymers makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or results obtained or obtainable using the Information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtain or obtainable on larger scale equipment. Full scale testing and end product use and performance are the responsibility of the Buyer. Buyer assumes all risk of use, storage and handling of product. Values reported as "typical" or stated within a range do not state minimum or maximum properties; consult Return Polymers representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. RETURN POLYMERS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.