



## RP2610 - White Cellular

**100% recycled WHITE Cellular PVC pulverized into a 20 mesh powder and blended in large quantities to ensure consistency. Primarily used as a in fence or sheet applications processed by twin screw extrusion. Third party blowing agent required for final product.**

General Property	Procedure / Method	Typical Value
<b>Form</b>		Pulverized Powder
<b>Color</b>	CIELab, D65, 10 degree observer or visual	White (L >88)
<b>Sieve Analysis</b>	% retention on 20 mesh	3%
	% retention on 120 mesh	97%
<b>Specific Gravity</b>	ASTM D-792	1.20 (Solid)
<b>Specific Gravity</b>	ASTM D-792	0.58 (foamed)
<b>Bulk Density</b>	ASTM D1895	18 lbs/ft <sup>3</sup>

Rev. 2.

Return Polymers makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or results obtained or obtainable using the Information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtain or obtainable on larger scale equipment. Full scale testing and end product use and performance are the responsibility of the Buyer. Buyer assumes all risk of use, storage and handling of product. Values reported as "typical" or stated within a range do not state minimum or maximum properties; consult Return Polymers representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. RETURN POLYMERS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.